

AISI THICKNESS TOLERANCE RANGES Galvanized Sheet

Gage Number	Thickness Inches		Lbs/Sq. Ft.	Gage Number	Thickness Inches		Lbs/Sq. Ft.
	Decimal Equiv	Tolerance Range	Weight Equiv		Decimal Equiv	Tolerance Range	Weight Equiv
10	0.1382	0.1472 0.1292	5.78125	21	0.0366	0.0406 0.0326	1.53125
11	0.1233	0.1323 0.1143	5.15625	22	0.0336	0.0376 0.0296	1.40625
12	0.1084	0.1174 0.0994	4.53125	23	0.0306	0.0346 0.0266	1.28125
13	0.0934	0.7014 0.0854	3.90525	24	0.0276	0.0316 0.0236	1.15625
14	0.0785	0.0865 0.0705	3.28125	25	0.0247	0.0287 0.0207	1.03125
15	0.071	0.077 0.065	2.96875	26	0.0217	0.0247 0.0187	0.90625
16	0.0635	0.0695 0.0575	2.65625	27	0.0202	0.0232 0.0172	0.64375
17	0.0575	0.0625 0.0525	2.40525	28	0.0187	0.0217 0.01202	0.78125
18	0.0516	0.0566 0.0466	2.15625	29	0.0172	0.0202 0.0142	0.71875
19	0.0456	0.0506 0.0406	1.90625	30	0.0157	0.0787 0.0727	0.65625
20	0.0396	0.0436 0.0356	1.65625				

Weight equivalents based on density of .2904 lb. per cubic inch.

Gages 10, 11, 12 - tolerances shown are for widths over 40" to 60" inclusive.

All other gages -- tolerances shown are for width over 32" to 60" inclusive.